



## INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

<b>(51) International Patent Classification <sup>6</sup> :</b> <b>A61L 15/46, 15/18, 9/01, 15/20</b>	<b>A1</b>	<b>(11) International Publication Number:</b> <b>WO 99/40953</b> <b>(43) International Publication Date:</b> 19 August 1999 (19.08.99)
<b>(21) International Application Number:</b> PCT/IB99/00185 <b>(22) International Filing Date:</b> 2 February 1999 (02.02.99) <b>(30) Priority Data:</b> 98102691.7      17 February 1998 (17.02.98)      EP <b>(71) Applicant (for all designated States except US):</b> THE PROCTER & GAMBLE COMPANY [US/US]; One Procter & Gamble Plaza, Cincinnati, OH 45202 (US). <b>(72) Inventor; and</b> <b>(75) Inventor/Applicant (for US only):</b> CORZANI, Italo [IT/IT]; Via Fontevecchia, 40, I-66100 Chieti (IT). <b>(74) Agents:</b> REED, T., David et al.; The Procter & Gamble Company, 5299 Spring Grove Avenue, Cincinnati, OH 45217-1087 (US).		<b>(81) Designated States:</b> AL, AM, AT, AT (Utility model), AU, AZ, BA, BB, BG, BR, BY, CA, CH, CN, CU, CZ, CZ (Utility model), DE, DE (Utility model), DK, DK (Utility model), EE, EE (Utility model), ES, FI, FI (Utility model), GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SK (Utility model), SL, TJ, TM, TR, TT, UA, UG, US, UZ, VN, YU, ZW, ARIPO patent (GH, GM, KE, LS, MW, SD, SZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GW, ML, MR, NE, SN, TD, TG).  <b>Published</b> <i>With international search report.</i>
<b>(54) Title:</b> DOPED ODOUR CONTROLLING MATERIALS  <b>(57) Abstract</b>  <p>An odour controlling material is disclosed for removing or reducing odour emanating from certain gaseous or liquid compounds which material comprises an inorganic absorbent material doped with one or more dopants which are selected from the gaseous or liquid compounds and derivatives thereof. Conventional adsorbent materials such as silica, alumina, silicates and aluminosilicates can be used and a gaseous or liquid compounds are preferably selected from fatty acids and derivatives thereof, amines and ammonia and salts thereof, alcohols, aldehydes and ketones and heterocompounds. The odour control material is suitable for incorporation in an absorbent article such as a pantiliner or a sanitary napkin.</p>		

**FOR THE PURPOSES OF INFORMATION ONLY**

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece	ML	Mali	TR	Turkey
BG	Bulgaria	HU	Hungary	MN	Mongolia	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MR	Mauritania	UA	Ukraine
BR	Brazil	IL	Israel	MW	Malawi	UG	Uganda
BY	Belarus	IS	Iceland	MX	Mexico	US	United States of America
CA	Canada	IT	Italy	NE	Niger	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NL	Netherlands	VN	Viet Nam
CG	Congo	KE	Kenya	NO	Norway	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NZ	New Zealand	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	PL	Poland		
CM	Cameroon	KR	Republic of Korea	PT	Portugal		
CN	China	KZ	Kazakhstan	RO	Romania		
CU	Cuba	LC	Saint Lucia	RU	Russian Federation		
CZ	Czech Republic	LI	Liechtenstein	SD	Sudan		
DE	Germany	LK	Sri Lanka	SE	Sweden		
DK	Denmark	LR	Liberia	SG	Singapore		
EE	Estonia						

## **DOPED ODOUR CONTROLLING MATERIALS**

This invention relates to an odour controlling material, and in particular to articles such as absorbent articles for absorbing bodily fluids, comprising the odour controlling material and to the use of an adsorbent material as an odour controlling material.

Malodours may be present in the environment from numerous sources both animate and inanimate. Many products and articles are available which aim to avoid or minimize the detection of such odours. This includes ventilation systems, room fresheners, car fresheners, and animal litter, for example. Indeed it is particularly desirable to provide odour controlling materials to address the malodours which are generated by the human body, or from bodily fluids such as perspiration, bad breath, urine, faeces, menstrual fluids and the like.

Absorbent articles for example are designed to be worn by humans to absorb bodily fluids, such as urine, menstrual fluid and perspiration, etc. Examples of absorbent articles include sanitary napkins, pantliners, disposable diapers, incontinence pads, tampons, perspiration pads and the like.

In use, the absorbent articles are known to acquire a variety of compounds, for example volatile fatty acids (e.g. isovaleric acid), ammonia, amines (e.g. triethylamine), sulfur containing compounds (e.g. mercaptans, sulphides), which release unpleasant odours. These compounds may be present in the bodily fluid or may be produced by fermentation once the bodily fluid is absorbed into the pad. In addition bodily fluids can contain microorganisms that can also generate malodorous by products. Unpleasant odours which emanate from absorbent pads when in use may make the wearer feel self conscious.

Various odour controlling materials have been disclosed. In particular, certain zeolitic materials are becoming known for their odour controlling

properties. Zeolitic materials are generally quite safe and have been found to control many odours associated with bodily fluids.

For example US Patent 4 304 675 discloses a powdered carpet treatment composition containing a natural or synthetic zeolite, preferably zeolite A. US Patent No 4 525 410 discloses a fiber article having antibacterial properties comprising zeolitic particles retaining therein at least one metal ion having bactericidal property and a mixed fiber assembly.

WO 81/01643 discloses the removal of ammonia and other toxic or potentially toxic nitrogenous irritants from diapers by incorporating into the diaper an inorganic aluminosilicate zeolite ammonium ion exchange material.

Active silica is also a known adsorbent material which is very efficient in extracting and storing various chemical species both from the liquid and gaseous phases.

In many applications, however, it would be desirable to enhance the adsorption power of the material, such as active silica, both in general terms and, specifically, in terms of selectivity with regard to particular chemical compounds. For example, in the case of hygienic articles containing an adsorbent material such as active silica or zeolite for adsorbing malodorous chemical species contained or generated in the physiological fluids.

Such malodorous compounds can be classified in various chemical groups such as low molecular weight fatty acids; ammonia and amines; alcohols, ketones and aldehydes; and heterocompounds particularly those containing sulfur or nitrogen atoms. Many of these compounds generate an extremely powerful odour which can clearly be detected by human olfaction even in amounts of a few parts per billion.

It is an object of the present invention to improve the adsorption power of these known adsorbent materials and specifically to improve their selectivity with regard to specific adsorbing power verses selected compounds.

According to the present invention there is provided an odour controlling material for removing or reducing odour emanating from certain gaseous or liquid compounds which comprises an inorganic adsorbent material doped with one or more dopants which are selected from the gaseous or liquid compounds and derivatives thereof, and compounds belonging to the same chemical class or having similar functionalities.

The adsorbent material may be, for example, silica, specifically active silica, alumina, silicates and natural and synthetic aluminosilicates such as zeolites, e.g. zeolite A.

By the present invention it has been surprisingly discovered that the adsorption capability of adsorbent materials can be significantly improved by doping with trace amounts of doping impurities which are selected from those compounds which have to be adsorbed or derivatives thereof or compounds of the same chemical class or having similar functionalities. These doping impurities can be broadly selected from fatty acids and derivatives thereof; ammonia and amines and their salts; alcohols, aldehydes and ketones; and heterocompounds.

The fatty acids are volatile fatty acids selected from straight chain and branched chain fatty acids containing, for example, from 1 to 12 carbon atoms, for example isovaleric acid. Another class of odorous compounds include ammonia and ammonium salts and amines having a boiling point of up to 170°C at atmospheric pressure and salts thereof, e.g. triethylamine.

A further class of odorous compounds comprises alcohols, aldehydes such as furaldehyde, and ketones having a boiling point of up to 170°C at

atmospheric pressure.

Another class of odorous materials include heterocompounds containing at least one nitrogen, sulfur or oxygen atom, preferably heterocyclic compounds containing one or two cyclic rings and containing one or two heteroatoms which may be the same or different. Other compounds in this category include mercapto- and thio-compounds and other compounds containing at least one sulphur atom per molecule which have a boiling point up to 170°C at atmospheric pressure.

According to the invention the doping impurity can be one of the malodorous compounds which has to be adsorbed. Alternatively, the doping impurity can be a derivative, such as a salt or ester, of the malodorous compound to be adsorbed. According to a further possibility the doping impurity can be a compound of the same chemical class or having the same functionalities as the compound to be adsorbed. For example, if valeric acid is the compound to be adsorbed the doping impurity can be any low molecular weight fatty acid such as butyric acid.

We have found that the improved adsorption is achieved with very small traces of the specific doping impurity or doping impurities. Concentrations of from 1 to 1000 parts per million by weight have been demonstrated to show significantly increased adsorbing power. Moreover, this improvement has been found to apply to the general adsorption power of the doped adsorbent material and also the selective adsorption in relation to specific classes of chemical compounds. A preferred concentration range is from 3 to 100 parts per million by weight and preferably from 10 to 50 parts per million by weight.

According to the present invention the adsorbent material can be doped with a number of different impurities or dopants selected from the same or different classes of compound. We have found that there are particular benefits in using a dopant which has more than one active group e.g. ammonium

butyrate which has both acid and ammonium groups. Such dopants may provide a synergy over two separate classes of compounds used as dopants.

According to one embodiment of the invention the adsorbent material is used at a neutral pH i.e. pH of  $7 \pm 0.5$ . However, according to other embodiments of the invention the pH of the adsorbent material can be adjusted according to the polar character of the malodorous substances. It is known that a strongly acid or a strongly basic adsorbent material, e.g. active silica, can be prepared to show an increased adsorbing power respectively with regard to basic and acid substances. However, this apparent higher adsorption is not a true adsorbent capability but is based on a chemical reaction so that the effect is transitory i.e. it is maintained only until the excess acidity or basicity, available for reaction, has been neutralized.

When the odour controlling material of the present invention is used for feminine hygiene, for example incorporated in a pantiliner or a sanitary napkin, it is preferred to provide the material with a neutral pH because malodorous compounds present in physiological fluids may be acidic, basic or neutral.

When used in other absorbent articles where the malodours have a defined and constant character, e.g. ammonia and amines originating from urine, the pH can be adjusted, in this case to an acidic pH to provide supplementary odour control to that provided by the doping impurities.

The doped adsorbent material can be prepared by any convenient known method. For example in the case of an adsorbent material comprising silica, silicagel or active silica can be prepared by precipitation as a gel from a solution of a soluble silicate by addition of an acid, such as sulphuric acid, or by flocculation of a colloidal solution of silica.

For example, the selected dopant or dopants are added to a solution of a soluble silicate at a temperature of, e.g. between 40 and 100°C, preferably

between 60 and 95°C. Sulphuric acid is added and the pH adjusted as required, preferably to a neutral pH. The mass is preferably maintained at a temperature of 60 to 95°C for a period of 10 to 30 minutes prior to the addition of a flocculant where the solution is a colloidal solution, followed by filtration or centrifugation and drying to yield the doped materials.

Conventional flocculating agents, which may be organic or inorganic, can be employed. Organic agents are preferred and especially Poly(ethylene oxide) polymers having molecular weights higher than 100,000 Daltons; polyethylene imine; surfactants such as benzalkonium and betaine derivatives.

Soluble silicates that are particularly useful as raw materials according to the present invention are those which, in the anhydrous form, may be described by the general formula:-  $\text{Me}_2\text{O} \cdot n\text{SiO}_2$  where  $0.5 \leq n \leq 4$  and Me is an alkali metal. We have found that the improved adsorbent properties are achieved independently of the method of production of the adsorbent material, e.g. active silica.

The pH of the material can be adjusted as desired. After drying, the resulting substantially amorphous silica retains an extremely porous structure even in the anhydrous state. The porous structure contributes to the adsorbing capability of the material towards both gaseous and liquid molecules.

The gelation or the formation of the colloidal solution of silica takes place, according to the present invention, in the presence of traces of the specific doping impurities e.g. in concentrations of from 1 to 1000, preferably 3 to 100 and most preferably 10 to 50 parts per million by weight.

The precipitates or gels of silica are dried until constant weight at a temperature between 80 and 1000°C, more preferably between 110 and 500°C and most preferably between 150 and 250°C.



The invention is illustrated by reference to the following Examples and Comparative Examples.

A reference active silica (DG 14) was prepared by the *Gel* process and dried at 190°C. Final pH was 7.10.

All other silica samples were prepared under the same conditions apart from the addition of selected doping impurities.

In the comparison of various active silicas for adsorbing power, two silicas were tested in parallel by flowing on them a stream of nitrogen containing a known concentration of a malodorous compound and measuring the adsorbed percent of that compound. The test method used was as follows:

#### **Test Method**

A glass cup was put in the bottom of a glass vessel of total volume of about 250 milliliters. The glass cup contained:

- 0.5 grams of active silica under test
- 0.5 grams of the "reference" malodorous compound solution i.e. a 2 % by weight water solution of butyric acid or a 5 % b.w. solution of trimethylamine.

Both solutions were buffered by adding 0.01 M of phosphate buffer; 0.0027 M of potassium chloride and 0.137 M of sodium chloride with an average pH=7.4.

A glass small pipe entered into the vessel arriving at about 1 cm over the blend of active silica and the above solution; through this glass pipe was flowing nitrogen at a flow rate regulated between 15 and 20 milliliters/minute.

The gas escaping from the vessel was passed through a "Draeger Tube" available from National Draeger Inc (USA) and used to adsorb and measure specific impurities contained as mixed gases or vapours in a main gas stream.

In particular, when the malodorous compound, was butyric acid we used as detector the Draeger tube 67 22101 whose scale is conventionally expressed in ppm of adsorbed acetic acid (kept as a reference material for volatile low molecular weight acids); while when the malodor was trimethylamine, we used the Draeger tube CH 20501 whose scale is conventionally expressed in ppm of adsorbed ammonia. The test is performed at 23°C.

It is clear that in any case the adsorption activity of the tested silica is inversely proportional to the malodorous compound detected by the Draeger tube.

In particular the adsorption ability of the tested active silica is kept inversely proportional to the quantity of malodourant compound escaped from the solution and detected by the Draeger tube after that a fixed flow rate of contaminated nitrogen has passed through the tube. Owing to the different capacity and sensitivity of the two used Draeger tube types, the reading of detected malodourant compound was made at different timings for butyric acid and for trimethylamine. More precisely, after having reached a steady state of flow of nitrogen and after having recorded the actual gaseous flow, the timer is started. The reading of impurities adsorbed by the tube is made:

- after the passage of 300 milliliters of nitrogen (so between 15 and 20 minutes of test when testing for butyric acid)
- after the passage of 1000 milliliters of nitrogen (so between 50 and 67 minutes of test when testing for trimethylamine).

#### **EXAMPLE 1**

A doped active silica (**DG 18**) was prepared under the same conditions as **DG 14** except that the gel was formed in the presence of 40 ppm of butyric acid. **DG 14** and **DG 18** were compared for activity in adsorbing malodorous low molecular weight fatty acids.

In the specific case they were tested as adsorption capability vs. the same butyric acid contained as vapour in a N<sub>2</sub> stream.

The result was that the doped material **DG 18** had adsorbed 2.18 times more (+ 118%) than the undoped **DG 14**.

#### **EXAMPLE 2**

Another doped silica (**DG 23**) was prepared and tested for butyric acid adsorption under the same conditions except that the gel was formed in the presence of 19 ppm of CH<sub>3</sub>(CH<sub>2</sub>)<sub>2</sub>COOH.

When compared with **DG 14** the doped material , **DG 23**, was shown to adsorb 13.3 times more volatile acid (+ 1230%).

#### **EXAMPLE 3**

A third silica doped with butyric acid (**DG 30**) was prepared in the presence of 10 ppm of impurity. This was compared with **DG 23** for adsorption of acids and was found to have 2.6 times less activity than **DG 23**.

It can be extrapolated from these results that **DG 30** is about 5.1 times more active (+ 410%) than **DG 14**. For doping with butyric acid and for the adsorption of volatile acids indicates an optimum value around a level of about 20 ppm of dopant.

#### **EXAMPLE 4**

For the adsorption of volatile acids, **DG 23** was compared with a commercial active silica, SYLOBLANC 82 available from Grace Co. **DG 23** was

found to adsorb 3.7 times (+ 270%) more than SYLOBLANC 82.

It is noted that in the tested form, SYLOBLANC 82 has a bulk density which is more than 5 times lower than **DG 23**. So it would be expected that for this reason only SYLOBLANC 82 would have a much higher specific surface, active for adsorption, and that the comparative tests between SYLOBLANC 82 and **DG 23** were not made under comparable conditions.

It is reasonable to expect that, if compared at the same bulk density, **DG 23** would have shown an even higher advantage over the commercial material.

#### **EXAMPLE 5**

An active silica (**DG 26**) was doped with 32 ppm of tri-methylamine. When used for the adsorption of the same amine in comparison with the undoped **DG 14**, **DG 26** was shown to adsorb 2.3 times more amine than the undoped material.

#### **EXAMPLE 6**

The same silica (**DG 26**) as in Example 5 was compared with another silica (**DG 27**) doped with 16 ppm of tri-methylamine. When compared for the adsorption of amines, looking for the optimum level of doping amine, **DG 26** revealed to be twice as effective as **DG 27**.

A further surprising phenomenon was shown for **DG 26**. When tested for the adsorption of volatile acids **DG 26** proved to be a very effective adsorber also for these materials even when the pH was neutral (pH=7.2).

All the above mentioned experiments show that it is possible to enhance the specific activity of an adsorbent active silica by doping it with traces of the same compound (or classes of compound) that must be preferentially adsorbed.

However, certain substances, such as tri-methylamine seem able to create an activation also versus other chemically different substances.

The present invention is not linked to any specific theory or supposed mechanism, but these results suggest that several mechanisms for achieving a higher and more selective adsorption capability are operable through the present method.

#### **EXAMPLE 7**

To confirm a possible synergy between different mechanisms, we prepared a silica (DG 32) doped with a compound having multifunctional groups.

The chosen compound was ammonium butyrate, because its molecule combines both types of supposed active groups investigated in these experiments.

It was added to the SiO<sub>2</sub> gel at a level of 20 ppm.

DG 32 was compared for adsorption of volatile acids with DG 23 (the previous best adsorber of acids, doped with 20 ppm of butyric acid).

It was actually found that DG 32 showed a further increase of adsorbing efficiency vs. DG 23 equal to + 80% (1.8 times more).

**What is claimed is:**

1. An odour controlling material for removing or reducing odour emanating from certain gaseous or liquid compounds which comprises an inorganic adsorbent material doped with one or more dopants which are selected from the gaseous or liquid compounds and derivatives thereof, and compounds belonging to the same chemical class or having similar functionalities.
2. An odour controlling material according to claim 1, wherein the adsorbent material is selected from silica, alumina, silicates and natural and synthetic alumino-silicates.
3. An odour controlling material according to claim 2, wherein the adsorbent material is active silica.
4. An odour controlling material according to any of claims 1 to 3, wherein the gaseous or liquid compounds are selected from fatty acids and derivatives thereof, amines and ammonia and salts thereof; alcohols, aldehydes and ketones and heterocompounds containing at least one of nitrogen, sulfur and oxygen.
5. An odour controlling material according to claim 4, wherein the fatty acids are selected from straight chain and branched chain fatty acids containing from 1 to 12 carbon atoms; alkali and alkaline earth metal salts thereof; esters thereof; ammonium salts and amides.
6. An odour controlling material according to claim 4, wherein the amines are selected from amines having a boiling point of up to 170°C at atmospheric pressure and salts thereof.

7. An odour controlling material according to claim 4, wherein the heterocompounds are selected from heterocyclic compounds containing one or two heteroatoms selected from nitrogen, sulfur and oxygen; mercapto- and thio-compounds and other compounds containing at least one sulfur atom per molecule and having a boiling point up to 170°C and atmospheric pressure.
8. An odour controlling material according to any of claims 1 to 7 which has a pH of  $7 \pm 0.5$ .
9. An odour controlling material according to any of claims 1 to 8 which comprises at least one dopant which has more than one active group.
10. A blend of odour control materials comprising two or more odour control materials according to any of claims 1 to 9.
11. An absorbent article having incorporated therein at least one odour controlling material according to any one of claims 1 to 10.
12. An absorbent article according to claim 11 which is a pantiliner or a sanitary napkin.
13. Use as an odour controlling material of an inorganic adsorbent material doped with one or more dopants selected from the compounds to be adsorbed and derivatives thereof, and compounds belonging to the same chemical class or having similar functionalities.

14. Use as an odour controlling material of an adsorbent material selected from silica, alumina, silicates and natural and synthetic aluminosilicates doped with one or more dopants selected from fatty acids and derivatives thereof; amine and ammonia and salts thereof; alcohols, aldehydes and ketones; and heterocompounds containing at least one of nitrogen, sulfur and oxygen.



# INTERNATIONAL SEARCH REPORT

Inter.      nal Application No

PCT/IB 99/00185

## A. CLASSIFICATION OF SUBJECT MATTER

IPC 6    A61L15/46    A61L15/18    A61L9/01    A61L15/20

According to International Patent Classification (IPC) or to both national classification and IPC

## B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 6    A61L

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

## C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	<p>DATABASE WPI Section Ch, Week 9329 Derwent Publications Ltd., London, GB; Class D22, AN 93-231547 XP002036165 &amp; JP 05 154187 A (MITSUBISHI MATERIALS CORP) see abstract</p> <p style="text-align: center;">---</p>	
A	<p>DATABASE WPI Section Ch, Week 8848 Derwent Publications Ltd., London, GB; Class D22, AN 88-341015 XP002071651 &amp; JP 63 252157 A (NIPPON KASEI KK) see abstract</p> <p style="text-align: center;">---</p> <p style="text-align: center;">-/--</p>	

☒ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

\* Special categories of cited documents:

"A" document defining the general state of the art which is not considered to be of particular relevance

"E" earlier document but published on or after the international filing date

"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

"O" document referring to an oral disclosure, use, exhibition or other means

"P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

"&" document member of the same patent family

Date of the actual completion of the international search

29 March 1999

Date of mailing of the international search report

07/04/1999

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2  
NL - 2280 HV Rijswijk  
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,  
Fax: (+31-70) 340-3016

Authorized officer

Cousins-Van Steen, G

# INTERNATIONAL SEARCH REPORT

International Application No

PCT/IB 99/00185

## C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	EP 0 103 214 A (KANEBO LTD ;KANTO KAGAKU (JP)) 21 March 1984 & US 4 525 410 A cited in the application ---	
A	WO 81 01643 A (MOLECULAR SIEVE SYSTEMS INC) 25 June 1981 cited in the application -----	

# INTERNATIONAL SEARCH REPORT

information on patent family members

International Application No

PCT/IB 99/00185

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
EP 0103214 A	21-03-1984	JP 1390178 C	23-07-1987
		JP 59037956 A	01-03-1984
		JP 61022977 B	03-06-1986
		CA 1225584 A	18-08-1987
		DE 3378673 A	19-01-1989
		US 4525410 A	25-06-1985
WO 8101643 A	25-06-1981	EP 0041569 A	16-12-1981